

Tender specifications OVER KERLITE 3plus collection

Supply of ceramic tiles made of Cotto d'Este Kerlite laminated porcelain tile for floors and walls.

Product characteristics

Cotto d'Este Kerlite laminated porcelain tiles, produced in a maximum size of 3000x1000 mm and 3mm thick, reinforced with fibreglass mesh, obtained from raw materials of the highest quality and purity (light clay, feldspar and ceramic pigments with high chromatic performance), and manufactured by dry pressing on a belt of atomized powder, subsequently sintered by means of industrial firing at temperatures exceeding 1200 °C.

The innovative Kerlite manufacturing process produces a final product which is light, flat and flexible, but at the same time compact, non-absorbent, frost-resistant, resistant to stains, chemical attack and thermal shock. The application of the fibreglass mesh gives the product high resistance and extreme versatility and ease of use for a wide range of applications in the architectural world.

Compliance with EN 14411-G / ISO 13006-G

The Over Kerlite 3plus collection is in compliance with the regulations required for first quality products in Italy and Europe UNI EN 14411-G and internationally through ISO 13006-G.

Quality and environmental certifications

The conservation of the product characteristics is guaranteed by the Quality Management System put into practice by Cotto d'Este in its plants and certified in accordance with UNI EN ISO 9001.

The collection is manufactured in plants with UNI EN ISO 14001 certified Environmental Management Systems (internationally recognised standard) and EMAS (Regulation 1221/09 - eco-management and audit community system).

The collection helps to meet the criteria for obtaining LEED credits. The product contains no VOC (volatile organic compounds). The Environmental Product Declaration (EPD) is available, this tool communicates clearly the environmental performances of the Over Kerlite 3plus collection based on its Life Cycle Assessment (LCA).

Commercial description of the product		
Company	COTTO D'ESTE (Panariagroup Industrie Ceramiche S.p.A.)	
Collection	OVER KERLITE 3plus	
Colours	OPENSACE, LOFT, OFFICE, ROAD	
Sizes	50X50cm NATURAL	-
	50X100cm NATURAL	-
	100X100cm NATURAL	100X100cm SOFT
	100X300cm NATURAL	100X300cm SOFT
Surfaces	NATURAL SOFT - Recommended for flooring in residential environments	
Edges	RECTIFIED	
Thickness	3,5mm	



EMAS



ISO 14001



LEED



LEED



ISO 9001



EN 14411
Le DOP sono disponibili sul sito internet www.cottodeste.it
DOP are available on the website www.cottodeste.it

CE MARK



MADE IN ITALY

Tender specifications OVER KERLITE 3plus collection

Technical features

Product type: laminated porcelain stoneware (UGL)

According to: ISO 13006-G (Group Bla), EN 14411-G (Group Bla)

Technical features		Test method	Required values ISO 13006-G, EN 14411-G	Average values OVER KERLITE 3plus
Water absorption		ISO 10545-3	≤ 0,5 %	0,1 (*) %
Modulus of rupture		ISO 10545-4	≥ 35 N/mm ²	50 N/mm ²
Deep abrasion resistance		ISO 10545-6	≤ 175mm ³	175mm ³
Linear thermal expansion		ISO 10545-8	No provision	$\alpha \leq 7 \cdot 10^{-6} \text{ } ^\circ\text{C}^{-1}$
Stain resistance		ISO 10545-14	Class 3 Min.	5 RESISTANT (Natural) ≥ 3 (Soft)
Chemical resistance (**)		ISO 10545-13	As indicated by manufacturer	LA, HA RESISTANT
Frost resistance		ISO 10545-12	No alteration	RESISTANT
Dimensions	Lenght and width	ISO 10545-2	± 0,6 % ± 2mm	COMPLIANT
	Straightness of sides	ISO 10545-2	± 0,5 % ± 1,5mm	COMPLIANT
	Rectangularity	ISO 10545-2	± 0,5 % ± 2mm	COMPLIANT
	Warpage	ISO 10545-2	± 0,5 % ± 2mm	COMPLIANT
	Thickness	ISO 10545-2	± 5 % ± 0,5mm	COMPLIANT
Slip resistance	DIN 51130	-	-	R9 (Natural)
	BCR-TORTUS	-	-	$\mu > 0,40$ (Natural)
	ANSI A326.3	-	-	DCOF ≥ 0.42 (Natural)
	UNE ENV 12633	-	-	Clase 1 (Natural)
Shade variation		ANSI A 137.1	As indicated by manufacturer	V1
Fire reaction		EN 13823	CPR (UE) 305/2011, 2000/147/CE, UNI EN 13501-1	Class A2-s1,d0 (wall)
		EN 9239-1		Class A2 _{fl} -s1 (floor)
Thermal conductivity		EN 12524	-	$\lambda = 1,3 \text{ W/m } ^\circ\text{K}$
Recommended minimum joint (***)		Indoor	-	1mm (wall) 2mm (floor)

(*) Average value referred to ceramic material only.

(**) Excluding hydrofluoric acid and its derivatives.

(***)The width of grout joints must be established by the installation supervisor, unless grout widths are regulated by national laying standards.

